



Product Data Sheet Item No. 3004-045

Guardrail Net 2.00 x 10.00 m

Schutzenetz24 GmbH
Weyerberg 5, DE-35614 Aßlar-Berghausen
Phone: +49 (0) 6443 - 436 96 40
Mail: office@safetynet365.com
Web: www.safetynet365.com



TECHNICAL DATA

Available Colors	green, blue, red, fastest availability
Dimensions	6' 7" x 32' 10"
Material	high tenacity polypropylene, knotless
Material Diameter	Ø 0.20" (316")
Mesh Size	1.8" x 1.8"
Pose of Meshes	quadratic (square)
Mesh Connection	knotless braid
Edge Design	reinforced selvage cord of approx. 38", with integral surround rope (sewn)
Max. Tensile Strength of a Mesh	720 lbf
Energy Absorption (approx.)	9.0 kJ
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	BG regulation no. 179, DGUV information 101-011, DGUV information 201-023, EN 1263-1
Certificate	DGUV Eurotest verification certificate 24100002, Oeko-Tex®; certificate 12.0.02466
Net Class	B1
Safety Net System	U (safety net in load-bearing construction for vertical use)
Regular Inspection Interval	12 months
Number of Test Meshes	3 pcs.
Continuous Operating Temperature	-40 to +175 °F
Melting Point	329 °F
Washing Temperature (max.)	80 °F
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%

Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalies	good/not good
Resistance to Organic Solvents	good
Resistance to Benzene and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	300 kly
Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	no contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	56081930
Area Density	13.25 oz/yd ²
Total Weight	17.86 lb