
## Product Data Sheet Item No. 3000-045

Guardrail Net by the m² (Custom-Made)

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Maii: office@safetynet365.com Web: www.safetynet365.com









| TECHNICAL DATA                                 |  |
|--|--|
| Available Colors                               | green, white, blue, black, anthracite, red, beige (hemp colored)                     |
| Material                                       | high tenacity polypropylene, knotless  |
| Material Diameter                              | Ø 0.20" (316")   |
| Mesh Size                                      | 1.8" x 1.8"  |
| Pose of Meshs                                  | quadratic (square)   |
| Mesh Connection                                | knotless braid   |
| Edge Design                                    | reinforced selvage cord of approx. 38", with integral surround rope (sewn)           |
| Max. Tensile Strength of a Mesh                | 720 lbf  |
| Energy Absorption (approx.)                    | 9.0 kJ   |
| Tensile Breaking Force Referred to Density     | 7.0 cN/den   |
| Breaking Elongation of Filament                | 15%  |
| Standards and Rules                            | BG regulation no. 179, DGUV information 101-011, DGUV information 201-023, EN 1263-1 |
| Certificate                                    | DGUV Eurotest verification certificate 24100002, Oeko-Tex® certificate 12.0.02466    |
| Net Class                                      | B1   |
| Safety Net System                              | U (safety net in load-bearing construction for vertical use)                         |
| Regular Inspection Interval                    | 12 months  |
| Number of Test Meshes                          | 3 pcs.   |
| Continuous Operating Temperature               | -40 to +175 °F   |
| Melting Point                                  | 329 °F   |
| Washing Temperature (max.)                     | 80 °F  |
| Yarn Moisture Regain                           | 0%   |
| Tensile Strength Reduction Because Of Moisture | 0%   |
| Resistance to Weak/Strong Acids                | very good/good   |

| Resistance to Weak/Strong Alkalis                       | good/not good                                 |
|---|---|
| Resistance to Organic Solvents                          | good  |
| Resistance to Benzine and Greases                       | very good                                     |
| Bending Strength & Abrasion Resistance                  | good  |
| Weather-Resistance                                      | good  |
| UV-Resistance   | 300 kly                                       |
| Tensile Strength After Two Years of Climatic Influences | 90%   |
| Elasticity After Years of Climatic Influences           | good long-term flexibility, little elongation |
| Flexibility When Used in Water                          | stays flexible                                |
| Contraction When Used in Water                          | low contraction                               |
| Contraction When Used Outside                           | no contraction                                |
| Behavior in High Heat / Fire                            | melting                                       |
| Electrical Characteristics                              | isolating, no electrical conductivity         |
| Customs Tariff No.                                      | 56081930                                      |
| Area Density  | 13.25 oz/yd²                                  |