## Product Data Sheet Item No. 9840-060

Safety Net with Stainless Steel Wire Core (per m²)

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Maii: office@safetynet365.com Web: www.safetynet365.com







| Available Colors                               | dark green   |
|--|--|
| Width  | 157.5"   |
| Material                                       | high tenacity polypropylene, knotless, stainless steel A2, stainless steel 1.4301    |
| Material Diameter                              | Ø 0.19" (316")   |
| Mesh Size                                      | 2.4" x 2.4"  |
| Pose of Meshes                                 | quadratic (square)   |
| Mesh Connection                                | knotless braid   |
| Rope Construction                              | 1 x 19   |
| Edge Design                                    | reinforced selvage cord of approx. 38"   |
| Max. Tensile Strength of a Mesh                | 550 lbf  |
| Breaking Elongation of Filament                | 15%  |
| Standards and Rules                            | EN 13501-1 (flame-retarding), classification B-s1 d2, DIN 4102 (B1, flame-retarding) |
| Continuous Operating Temperature               | -40 to +175 °F   |
| Melting Point                                  | 329 °F   |
| Yarn Moisture Regain                           | 0%   |
| Tensile Strength Reduction Because Of Moisture | 0%   |
| Resistance to Weak/Strong Acids                | very good/good   |
| Resistance to Weak/Strong Alkalis              | good/not good  |
| Resistance to Organic Solvents                 | good   |
| Resistance to Benzine and Greases              | very good  |
| Bending Strength & Abrasion Resistance         | good   |
| Weather-Resistance                             | good   |
| UV-Resistance                                  | 300 kly  |
| Elasticity After Years of Climatic Influences  | good long-term flexibility, no elongation  |
|  |  |

| Flexibility When Used in Water | stays flexible                                  |
|--------------------------------|---|
| Contraction When Used in Water | no contraction                                  |
| Contraction When Used Outside  | no contraction                                  |
| Behavior in High Heat / Fire   | melting   |
| Electrical Characteristics     | isolating coating, electrically conducting core |
| Customs Tariff No.             | 56081930  |
| Area Density                   | 15.25 oz/yd²                                    |