
Product Data Sheet Item No. 2369-045-01

Cargo Net 2.70 x 4.10 m

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Maii: office@safetynet365.com Web: www.safetynet365.com









| TE | $M \cap A$ | \ I | \triangle \vee - | T / |
|----|--------------|-----|----------------------|-----|
| | NIII . 4 | 7 I | 1 1 4 | 1 4 |

| Available Colors | green | | |
|------------------------------------------------|---------------------------------------------------------------|--|--|
| Dimensions | 8' 10" x 13' 5" | | |
| Material | high tenacity polypropylene, knotless | | |
| Material Diameter | Ø 0.12" (18") | | |
| Mesh Size | 1.8" x 1.8" | | |
| Pose of Meshs | quadratic (square) | | |
| Mesh Connection | knotless braid | | |
| Edge Design | reinforced selvage cord of approx. 14" | | |
| Shock Cord | incl. pulled in shock cord, Ø 14" | | |
| Max. Tensile Strength of a Mesh | 280 lbf | | |
| Tensile Breaking Force Referred to Density | 7.0 cN/den | | |
| Breaking Elongation of Filament | 15% | | |
| Standards and Rules | VDI standard 2700 | | |
| Certificate | DEKRA certificate 200921463, Oeko-Tex® certificate 12.0.02466 | | |
| Continuous Operating Temperature | -40 to +175 °F | | |
| Melting Point | 329 °F | | |
| Washing Temperature (max.) | 80 °F | | |
| Yarn Moisture Regain | 0% | | |
| Tensile Strength Reduction Because Of Moisture | 0% | | |
| Resistance to Weak/Strong Acids | very good/good | | |
| Resistance to Weak/Strong Alkalis | good/not good | | |
| Resistance to Organic Solvents | good | | |
| Resistance to Benzine and Greases | very good | | |
| Bending Strength & Abrasion Resistance | good | | |
| | | | |

| Weather-Resistance | good |
|---------------------------------------------------------|-----------------------------------------------|
| UV-Resistance | 300 kly |
| Tensile Strength After Two Years of Climatic Influences | 90% |
| Elasticity After Years of Climatic Influences | good long-term flexibility, little elongation |
| Flexibility When Used in Water | stays flexible |
| Contraction When Used in Water | low contraction |
| Contraction When Used Outside | no contraction |
| Behavior in High Heat / Fire | melting |
| Electrical Characteristics | isolating, no electrical conductivity |
| Customs Tariff No. | 56081930 |
| Area Density | 4.40 oz/yd² |
| Total Weight | 5.73 lb |