Y

Max. Tensile Strength of a Mesh	130 lbf
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	VDI standard 2700
Certificate	Oeko-Tex® certificate 12.0.02466
Continuous Operating Temperature	-40 to +175 °F
Melting Point	329 °F
Washing Temperature (max.)	80 °F
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/not good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good

Container Net 3.50 x 5.00 m

le b

black

Ø 0.07"

0.8" x 0.8"

quadratic (square)

knotless braid

11' 6" x 16' 5"

high tenacity polypropylene, knotless

reinforced selvage cord of approx. 14"

TECHNICAL DATA

Available Colors

Material Diameter

Pose of Meshs

Edge Design

Mesh Connection

Dimensions Material

Mesh Size





Schutznetze24 GmbH

Weyerberg 5, DE-35614 Aßlar-Berghausen

Phone: +49 (0) 6443 - 436 96 40

Mail: office@safetynet365.com Web: www.safetynet365.com

UV-Resistance	300 kly
Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	no contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	56081930
Area Density	3.85 oz/yd²
Total Weight	5.95 lb