Product Data Sheet Item No. 212-045

High Level Rack Safety Net (Custom-Made)

				-
				Game
COL MON	Calif Days	-	and sa	

TECHNICAL DATA

Available Colors	green, white, blue, black, anthracite, red, beige (hemp colored)
Material	high tenacity polypropylene, knotless
Material Diameter	Ø 0.20" (316")
Mesh Size	1.8" x 1.8"
Pose of Meshs	quadratic (square)
Mesh Connection	knotless braid
Edge Design	reinforced selvage cord of approx. 14"
Max. Tensile Strength of a Mesh	720 lbf
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	ASR 12/1-3, ASR 17/1,2, DGUV standard 101-011, DGUV rule 108-007 (formerly BG regulation
	no. 234)
Certificate	Oeko-Tex® certificate 12.0.02466
Regular Inspection Interval	12 months
Number of Test Meshes	3 pcs.
Continuous Operating Temperature	-40 to +175 °F
Continuous Operating Temperature Melting Point	-40 to +175 °F 329 °F
Melting Point	329 °F
Melting Point Washing Temperature (max.)	329 °F 80 °F
Melting Point Washing Temperature (max.) Yarn Moisture Regain	329 °F 80 °F 0%
Melting Point Washing Temperature (max.) Yarn Moisture Regain Tensile Strength Reduction Because Of Moisture	329 °F 80 °F 0% 0%
Melting Point Washing Temperature (max.) Yarn Moisture Regain Tensile Strength Reduction Because Of Moisture Resistance to Weak/Strong Acids	329 °F 80 °F 0% 0% very good/good Very good/good
Melting Point Washing Temperature (max.) Yarn Moisture Regain Tensile Strength Reduction Because Of Moisture Resistance to Weak/Strong Acids Resistance to Weak/Strong Alkalis	329 °F 80 °F 0% 0% very good/good good/not good

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Mail: office@safetynet365.com Web: www.safetynet365.com





Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	300 kly
Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	no contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	56081930
Area Density	11.80 oz/yd²