## Product Data Sheet Item No. 72061-015

Air-Permeable Container Cover Sheet 3.50  $\times$  6.00 m

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Mail: office@safetynet365.com Web: www.safetynet365.com







Available Colorsdark greenDimensions11' 6" x 19' 8"MaterialpolyethyleneType of Textileclosemesh fabric panels, air and water permeableMesh Size0.04" x 0.12"Shading50%Edge Designwith reinforced and stitched edges all around (approx. 1.12" wide)Eyeletsinside diameter Ø 58", all around, with chosen spacing (standard every 20")
Material       polyethylene         Type of Textile       closemesh fabric panels, air and water permeable         Mesh Size       0.04" x 0.12"         Shading       50%         Edge Design       with reinforced and stitched edges all around (approx. 1.12" wide)
Type of Textile closemesh fabric panels, air and water permeable  Mesh Size 0.04" x 0.12"  Shading 50%  Edge Design with reinforced and stitched edges all around (approx. 1.12" wide)
Mesh Size 0.04" x 0.12"  Shading 50%  Edge Design with reinforced and stitched edges all around (approx. 1.12" wide)
Shading 50%  Edge Design with reinforced and stitched edges all around (approx. 1.12" wide)
Edge Design with reinforced and stitched edges all around (approx. 1.12" wide)
Eyelets inside diameter Ø 58", all around, with chosen spacing (standard every 20")
Shock Cord incl. pulled in shock cord, Ø 14"
Breaking Force 130 lbf (average lengthways)
Breaking Elongation of Filament 15%
Standards and Rules VDI standard 2700
Certificate Oeko-Tex® certificate 12.0.02466
Continuous Operating Temperature -20 to +140 °F
Melting Point 311 °F
Yarn Moisture Regain 0%
Tensile Strength Reduction Because Of Moisture 0%
Resistance to Weak/Strong Acids very good/good
Resistance to Weak/Strong Alkalis good/good
Resistance to Organic Solvents good
Resistance to Benzine and Greases very good
Bending Strength & Abrasion Resistance good
Weather-Resistance good
UV-Resistance 250 kly

Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, no elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	low contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	63079010
Area Density	5.90 oz/yd²
Total Weight	14.33 lb