


Product Data Sheet Item No. 19043-100

Fall Safety Net 7.50 x 15.00 m

Schutznetze24 GmbH
Weyerberg 5, DE-35614 Aßlar-Berghausen
Phone: +49 (0) 6443 - 436 96 40
Mail: office@safetynet365.com
Web: www.safetynet365.com



TECHNICAL DATA

| | |
|--|---|
| Available Colors | green, blue, fastest availability |
| Dimensions | 24' 7" x 49' 3" |
| Material | high tenacity polypropylene, knotless |
| Material Diameter | Ø 0.19" (316") |
| Mesh Size | 4.0" x 4.0" |
| Pose of Meshs | quadratic (square) |
| Mesh Connection | knotless braid |
| Edge Design | reinforced selvedge cord of approx. 38", with edged rope |
| Max. Tensile Strength of a Mesh | 670 lbf |
| Energy Absorption (approx.) | 4.6 kJ |
| Tensile Strength of Edged Rope | 6,700 lbf |
| Tensile Breaking Force Referred to Density | 7.0 cN/den |
| Breaking Elongation of Filament | 15% |
| Standards and Rules | BG regulation no. 179, DGUV standard 101-011, EN 1263-1 |
| Certificate | GS verification certificate 23100032, Oeko-Tex®; certificate 12.0.02466 |
| Net Class | A2 |
| Safety Net System | S (rope-edged safety net) |
| Regular Inspection Interval | 12 months |
| Number of Test Meshes | 3 pcs. |
| Continuous Operating Temperature | -40 to +175 °F |
| Melting Point | 329 °F |
| Washing Temperature (max.) | 80 °F |
| Yarn Moisture Regain | 0% |

| | |
|--|---|
| Tensile Strength Reduction Because Of Moisture | 0% |
| Resistance to Weak/Strong Acids | very good/good |
| Resistance to Weak/Strong Alkalis | good/not good |
| Resistance to Organic Solvents | good |
| Resistance to Benzine and Greases | very good |
| Bending Strength & Abrasion Resistance | good |
| Weather-Resistance | good |
| UV-Resistance | 300 kly |
| Tensile Strength After Two Years of Climatic Influences | 90% |
| Elasticity After Years of Climatic Influences | good long-term flexibility, little elongation |
| Flexibility When Used in Water | stays flexible |
| Contraction When Used in Water | low contraction |
| Contraction When Used Outside | no contraction |
| Behavior in High Heat / Fire | melting |
| Electrical Characteristics | isolating, no electrical conductivity |
| Customs Tariff No. | 56081930 |
| Area Density | 8.10 oz/yd ² |
| Total Weight | 52.59 lb |