

# Product Data Sheet Item No. 771

## Archery Backstop Netting by the m<sup>2</sup>

(Custom-Made)

Schutznetze24 GmbH  
Weyerberg 5, DE-35614 Aßlar-Berghausen  
Phone: +49 (0) 6443 - 436 96 40  
Mail: [office@safetynet365.com](mailto:office@safetynet365.com)  
Web: [www.safetynet365.com](http://www.safetynet365.com)



### TECHNICAL DATA

Available Colors	green, white, blue, black
Material	high tenacity polypropylene, flame-retardant, woven tight
Type of Textile	polypropylene monofilament
Mesh Size	0.04" x 0.04"
Production Tolerance	external dimensions: $\pm 1"$
Shading	98%
Wind Reduction	98%
Edge Design	seamed (left and right edge approx. 1" wide) with eyelets on top side
Eyelets	Stainless steel eyelets ( $\varnothing 5/16"$ ) with snap hooks ( $\varnothing 1.12"$ ), fastened along the top border at intervals of approx. 12"
Breaking Elongation of Filament	15%
Standards and Rules	DIN 4102 (B1, flame-retarding)
Continuous Operating Temperature	-40 to +175 °F
Melting Point	329 °F
Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/not good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	250 kly
Tensile Strength After Two Years of Climatic Influences	90%

<b>Elasticity After Years of Climatic Influences</b>	good long-term flexibility, no elongation
<b>Flexibility When Used in Water</b>	stays flexible
<b>Contraction When Used in Water</b>	low contraction
<b>Contraction When Used Outside</b>	low contraction
<b>Behavior in High Heat / Fire</b>	melting
<b>Electrical Characteristics</b>	isolating, no electrical conductivity
<b>Customs Tariff No.</b>	95069990
<b>Area Density</b>	15.05 oz/yd <sup>2</sup>