
Product Data Sheet Item No. 2492-045-01

Cargo Net 3.00 x 3.50 m

Schutznetze24 GmbH Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Maii: office@safetynet365.com Web: www.safetynet365.com









| т | \bigcirc | | N | 10 | ~ A | I. | | Λ- | ГΑ |
|-----|------------|---|-----|----|-----|----|-------|----|----|
| - 1 | ارا | _ | IVI | ш | , F | ۱ı | - 1) | А | IΑ |

| Available Colors | green | | | | |
|--|---|--|--|--|--|
| Dimensions | 9' 10" x 11' 6" | | | | |
| Material | high tenacity polypropylene, knotless | | | | |
| Material Diameter | Ø 0.09" | | | | |
| Mesh Size | 1.8" x 1.8" | | | | |
| Pose of Meshs | quadratic (square) | | | | |
| Mesh Connection | knotless braid | | | | |
| Edge Design | reinforced selvage cord of approx. 14" | | | | |
| Max. Tensile Strength of a Mesh | 180 lbf | | | | |
| Tensile Breaking Force Referred to Density | 7.0 cN/den | | | | |
| Breaking Elongation of Filament | 15% | | | | |
| Standards and Rules | VDI standard 2700 | | | | |
| Certificate | DEKRA certificate 201125785, Oeko-Tex® certificate 12.0.02466 | | | | |
| Continuous Operating Temperature | -40 to +175 °F | | | | |
| Melting Point | 329 °F | | | | |
| Washing Temperature (max.) | 80 °F | | | | |
| Yarn Moisture Regain | 0% | | | | |
| Tensile Strength Reduction Because Of Moisture | 0% | | | | |
| Resistance to Weak/Strong Acids | very good/good | | | | |
| Resistance to Weak/Strong Alkalis | good/not good | | | | |
| Resistance to Organic Solvents | good | | | | |
| Resistance to Benzine and Greases | very good | | | | |
| Bending Strength & Abrasion Resistance | good | | | | |
| Weather-Resistance | good | | | | |
| | | | | | |

| UV-Resistance | 300 kly |
|---|---|
| Tensile Strength After Two Years of Climatic Influences | 90% |
| Elasticity After Years of Climatic Influences | good long-term flexibility, little elongation |
| Flexibility When Used in Water | stays flexible |
| Contraction When Used in Water | low contraction |
| Contraction When Used Outside | no contraction |
| Behavior in High Heat / Fire | melting |
| Electrical Characteristics | isolating, no electrical conductivity |
| Customs Tariff No. | 56081930 |
| Area Density | 2.65 oz/yd² |
| Total Weight | 2.32 lb |