Product Data Sheet Item No. 1903-100/2007-020 Weyerberg 5, DE-35614 Aßlar-Berghausen Phone: +49 (0) 6443 - 436 96 40 Mail: office@safetynet365.com Web: www.safetynet365.com









| TECHNICAL DATA                                 |  |
|--|--|
| Material                                       | high tenacity polypropylene, knotless                                  |
| Material Diameter                              | Ø 0.07", Ø 0.20" (316")  |
| Mesh Size                                      | 0.8" x 0.8", 4.0" x 4.0"   |
| Pose of Meshes                                 | quadratic (square)   |
| Mesh Connection                                | knotless braid   |
| Edge Design                                    | reinforced selvage cord of approx. 38", with edged rope                |
| Edged Rope                                     | polysteel rope (Ø 12", white), all around                              |
| Max. Tensile Strength of a Mesh                | 720 lbf  |
| Energy Absorption (approx.)                    | 4.8 kJ   |
| Tensile Strength of Edged Rope                 | 6,700 lbf  |
| Tensile Breaking Force Referred to Density     | 7.0 cN/den   |
| Breaking Elongation of Filament                | 15%  |
| Standards and Rules                            | BG regulation no. 179, DGUV standard 101-011, EN 1263-1                |
| Certificate                                    | GS verification certificate 23100030, Oeko-Tex® certificate 12.0.02466 |
| Net Class                                      | A2   |
| Safety Net System                              | S (rope-edged safety net)  |
| Regular Inspection Interval                    | 12 months  |
| Number of Test Meshes                          | 3 pcs.   |
| Washing Temperature (max.)                     | 80 °F  |
| Yarn Moisture Regain                           | 0%   |
| Tensile Strength Reduction Because Of Moisture | 0%   |
| Weather-Resistance                             | good   |
| UV-Resistance                                  | 300 kly  |
| Elasticity After Years of Climatic Influences  | good long-term flexibility, little elongation                          |

| Flexibility When Used in Water | stays flexible                        |
|--------------------------------|---------------------------------------|
| Contraction When Used in Water | low contraction                       |
| Contraction When Used Outside  | no contraction                        |
| Electrical Characteristics     | isolating, no electrical conductivity |
| Customs Tariff No.             | 56081930                              |
| Area Density                   | 11.95 oz/yd²                          |