


**Product Data Sheet Item No. 1903-045**  
**Custom-Made Working Platform Net DGUV**  
**201-010**

Schutznetze24 GmbH  
Weyerberg 5, DE-35614 Aßlar-Berghausen  
Phone: +49 (0) 6443 - 436 96 40  
Mail: office@safetynet365.com  
Web: www.safetynet365.com



**TECHNICAL DATA**

<b>Available Colors</b>	green, white, blue, black, anthracite, red, beige (hemp colored)
<b>Material</b>	high tenacity polypropylene, knotless
<b>Material Diameter</b>	Ø 0.20" (316")
<b>Mesh Size</b>	1.8" x 1.8"
<b>Pose of Meshes</b>	quadratic (square)
<b>Mesh Connection</b>	knotless braid
<b>Edge Design</b>	reinforced selvage cord of approx. 38", with edged rope
<b>Edged Rope</b>	polysteel rope (Ø 12", white), all around
<b>Max. Tensile Strength of a Mesh</b>	720 lbf
<b>Energy Absorption (approx.)</b>	9.0 kJ
<b>Tensile Strength of Edged Rope</b>	6,700 lbf
<b>Tensile Breaking Force Referred to Density</b>	7.0 cN/den
<b>Breaking Elongation of Filament</b>	15%
<b>Standards and Rules</b>	BG regulation no. 179, DGUV standard 101-011, DGUV information 201-010 (formerly BGI 662), EN 1263-1
<b>Certificate</b>	GS verification certificate 23100027, Oeko-Tex®; certificate 12.0.02466
<b>Net Class</b>	B1
<b>Safety Net System</b>	S (rope-edged safety net)
<b>Regular Inspection Interval</b>	12 months
<b>Number of Test Meshes</b>	3 pcs.
<b>Continuous Operating Temperature</b>	-40 to +175 °F
<b>Melting Point</b>	329 °F
<b>Washing Temperature (max.)</b>	80 °F

Yarn Moisture Regain	0%
Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/not good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	300 kly
Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Flexibility When Used in Water	stays flexible
Contraction When Used in Water	low contraction
Contraction When Used Outside	no contraction
Behavior in High Heat / Fire	melting
Electrical Characteristics	isolating, no electrical conductivity
Customs Tariff No.	56081930
Area Density	14.00 oz/yd <sup>2</sup>