## Product Data Sheet Item No. 3006-060GSV

The second second

Guardrail Net 2.00 x 5.00 m with Quick-Release Straps

SY	
	 8010
	N N
	N N

## TECHNICAL DATA

Available Colors	green, blue, fastest availability
Dimensions	6' 7" x 16' 5"
Material	high tenacity polypropylene, knotless
Material Diameter	Ø 0.20" (316")
Mesh Size	2.4" x 2.4"
Pose of Meshs	quadratic (square)
Mesh Connection	knotless braid
Edge Design	reinforced selvage cord of approx. 38", with integral surround rope and sewn straps with self
	locking buckle (at an interval of 30" max., length approx. 20"
Max. Tensile Strength of a Mesh	720 lbf
Energy Absorption (approx.)	6.1 kJ
Tensile Strength of Buckle Straps	breaking load when used as restraint: 1,100 lbf
Tensile Breaking Force Referred to Density	7.0 cN/den
Breaking Elongation of Filament	15%
Standards and Rules	BG regulation no. 179, DGUV information 101-011, DGUV information 201-023, EN 1263-1
Certificate	DGUV Eurotest verification certificate 24100006, Oeko-Tex® certificate 12.0.02466
Net Clean	
Net Class	A1
Net Class Safety Net System	A1 U (safety net in load-bearing construction for vertical use)
Safety Net System	U (safety net in load-bearing construction for vertical use)
Safety Net System Regular Inspection Interval	U (safety net in load-bearing construction for vertical use) 12 months
Safety Net System Regular Inspection Interval Number of Test Meshes	U (safety net in load-bearing construction for vertical use) 12 months 3 pcs.
Safety Net System Regular Inspection Interval Number of Test Meshes Continuous Operating Temperature	U (safety net in load-bearing construction for vertical use) 12 months 3 pcs. -40 to +175 °F
Safety Net System Regular Inspection Interval Number of Test Meshes Continuous Operating Temperature Melting Point	U (safety net in load-bearing construction for vertical use) 12 months 3 pcs. -40 to +175 °F 329 °F



Schutznetze24 GmbH

Weyerberg 5, DE-35614 Aßlar-Berghausen

Phone: +49 (0) 6443 - 436 96 40

Mail: office@safetynet365.com Web: www.safetynet365.com





Tensile Strength Reduction Because Of Moisture	0%
Resistance to Weak/Strong Acids	very good/good
Resistance to Weak/Strong Alkalis	good/not good
Resistance to Organic Solvents	good
Resistance to Benzine and Greases	very good
Bending Strength & Abrasion Resistance	good
Weather-Resistance	good
UV-Resistance	300 kly
Tensile Strength After Two Years of Climatic Influences	90%
Elasticity After Years of Climatic Influences	good long-term flexibility, little elongation
Elasticity After Years of Climatic Influences Flexibility When Used in Water	good long-term flexibility, little elongation stays flexible
·	
Flexibility When Used in Water	stays flexible
Flexibility When Used in Water Contraction When Used in Water	stays flexible low contraction
Flexibility When Used in Water Contraction When Used in Water Contraction When Used Outside	stays flexible low contraction no contraction
Flexibility When Used in Water Contraction When Used in Water Contraction When Used Outside Behavior in High Heat / Fire	stays flexible low contraction no contraction melting
Flexibility When Used in Water Contraction When Used in Water Contraction When Used Outside Behavior in High Heat / Fire Electrical Characteristics	stays flexible low contraction no contraction melting isolating, no electrical conductivity